



KITTEN

BELNED GLASS & GLAZING
PRODUCTS

NL

Ramgatseweg 6, 4941 VS Raamsdonksveer
T +31 (0)162 576 576 • verkoop@belned.nl

BE

Industriezone Centrum Zuid 3041, B-3530 Houthalen
T +32 (0)11 525 880 • sales@belned.be

WWW.BELNED.NL

TECHNICAL DATA PU-GUNFOAM LOW EXPANSION

PRODUCT DESCRIPTION

PU Gunfoam Low Expansion is a high-quality, moisture-curing polyurethane gun foam with very low expansion behaviour. The product is particularly suitable for use in pressure-sensitive structures, such as installing windows, insulating and fixing electrical installations and cable runs in walls. The special formulation achieves an increased foam yield. This product has been manufactured under the controls established by an audited quality management system that conforms to ISO 9001:2015.

PRODUCT BENEFITS

- very low expansion behaviour (< 30%)
- very low expansion pressure during curing (0.1 kPa)
- very good dimensional stability
- fine cell structure
- for filling, sealing and insulating
- very low emission (GEV EMICODE EC1 Plus)
- French VOC-Emission Class A+
- Foam Yield (750 ml): up to 50 Litres

AREAS OF APPLICATION

- Window mounting (for clean and controlled backfill as well as insulating and sealing window seams and rolling shutter housings)
- Filling and insulation of joints and cavities in roof extensions and roof insulation
- Filling smaller wall recesses, conduit penetrations of any kind and other cavities.

PRODUCT FEATURES

PU Gunfoam Low Expansion adheres to all common building materials except polyethylene, silicone, oils and greases, mould release agents or similar substances. The foam can be used at surface and ambient temperatures of +5°C to +35°C. Cured foam is predominantly closed-celled, rot-proof, moisture- and temperature-resistant from -40°C to +80°C. It is aging resistant, however not against UV radiation.

WORK PREPARATION

Surface must be firm, clean, dust and grease free. Remove loose particles **and dampen the immediate area with water before proceeding**. As an option, using a primer will increase stability. Have all components ready for attachment. Have the PU-Cleaner ready for cleaning and removal of fresh foam. The ideal working temperature is +20°C. Cans that are too cold can be carefully heated in lukewarm water. **Attention: Never heat above +50°C, as the can may burst. Cans that are too hot, such as those left in a car during summer, can be cooled in cold water, but do not shake!** Follow the gun operating instructions. Before connecting with the foam gun, **shake the can about 30x**. Placing the can on a surface, attach the gun by screwing it onto the threaded collar of the can. Do not tilt or overtorque the threaded adapter. Repeat the shaking after longer interruptions.

APPLICATION

Fill voids modestly, as fresh foam can expand by about 30%. Foam is dispensed by squeezing the trigger. **Apply moisture evenly to the discharged foam. For larger gaps and cavities moistening is recommended after each foam layer.** Applying insufficient moisture and/or cavity overfilling may lead to subsequent unintended foam expansion. After the application is finished, any foam left on the foam gun should be cleaned immediately with PU-Cleaner. Cured foam can only be removed by mechanical means. **If the can isn't empty, leave the foam gun connected until the next application!** An opened can should be used within 4 weeks. Once the can is completely empty, remove the gun carefully and clean the outside with PU-Cleaner immediately. Then connect a can of PU-Cleaner to the gun and press the trigger several times to rinse the gun's inner parts with pointing the nozzle into an appropriate receiving container. **Caution: The cleaner is dispensed under high pressure!**



KITTEN

BELNED GLASS & GLAZING PRODUCTS



Ramgatseweg 6, 4941 VS Raamsdonksveer
T +31 (0)162 576 576 • verkoop@belned.nl



Industriezone Centrum Zuid 3041, B-3530 Houthalen
T +32 (0)11 525 880 • sales@belned.be

WWW.BELNED.NL

SHELF LIFE & STORAGE

Standard Valve System (VPG01): 12 months / Safety Valve System (VKS01 / VKS02): 15 months.

The ideal storage temperature is between +10 and +20°C. Considerably higher temperatures may reduce the shelf-life. Cans must be stored **upright** and protected from humidity, frost and heat.

Empty cans should be disposed of in accordance with national regulations.

SAFETY INSTRUCTIONS

Safety Data Sheet is available.

TECHNICAL DATA

Measured at + 23°C, 50% relative humidity, according to FEICA test methods & EN 17333.

Application temperatures (surfaces and ambient)	minimum	+ 5°C	Post expansion (35-mm-joint width) (FEICA TM 1010)	dry	< 30 %
	optimal	+ 20°C			
	maximum	+ 35°C			
Application temperatures of can	minimum	+ 5°C	Tensile strength (FEICA TM 1018)	dry	~ 125 kPa
	maximum	+ 30°C		moist	~ 105 kPa
Foam colour	yellowish		Elongation at break (FEICA TM 1018)	dry	~ 10 %
Cell structure	medium to fine			moist	~ 11 %
Free foamed density (FEICA TM 1019)	dry	~ 19 kg/m ³	Shear strength (FEICA TM1012)	moist	~ 40 kPa
Tack free time (FEICA TM 1014)	dry	~12 min		dry	~ 40 kPa
Cutting time (FEICA TM 1005)	dry	~ 55 min	Compression strength (at 10% compression) (FEICA TM 1011)	moist	~ 30 kPa
				Curing pressure (during curing process) (FEICA TM 1009)	after 2.5 h
Fully loadable (30 mm bead)	~ 12 hours		Temperature resistance of a cured foam	- 40°C to +80°C (short term up to +100°C)	
Sagging behaviour and max. joint width (FEICA TM 1006)	dry (+5°C)	Level 1 up to 60 mm	GEV EMICODE	EC1 PLUS very low emission	
Joint yield (FEICA TM 1002; dry application)	750 ml	up to 27 m	French VOC-Emission Class	A+	
Foam yield (box-test) (FEICA TM 1003 / moist application)	750 ml	up to 50 litres	Construction Material Class according to EN 13501-1	F	
Brittleness (FEICA TM 1008 / dry application)	+5°C / 1.5h / 24h	1 / 1	Construction Material Class according to DIN 4102 Part 1	B3	
Dimensional stability (FEICA TM 1004)	dry	± 5 %			
	moist	± 5 %			

The information in this data sheet represents laboratory values that may vary based on actual application, and thus represent no guarantee of a given attribute. The variety of specific applications and possible combinations cannot be covered in this description. The user is responsible to gather information accordingly. Specific results cannot be guaranteed due to lack of oversight of application requirements. Tests performed by the individual user are expressly advised in order to achieve the desired results